



# Technical Data Sheet

**JESSUP #3335 Safety Track®**

TDS number: 3335  
Effective Date: 4/16/2009

## DESCRIPTION

Jessup 3335 Yellow Safety Track® is a commercial grade aluminum oxide non-slip tape that has been designed to meet OSHA standards for general-purpose anti-slip surface applications.

## APPLICATIONS

Jessup 3335 Yellow Safety Track® is designed for indoor and outdoor non-skid applications that require long-term anchorage to a wide variety of surfaces. It has been successfully used in a wide range of markets including OEM, Action Sports and Building Safety. It is NFSI certified for “High Traction”.

## PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	PSTC - 133 - Substrate - Pressure Sensitive adhesive - Release Liner	0.025 inch (0.635 mm) 0.002 inch (0.051 mm) 0.006 inch (0.152 mm)
Peel Adhesion to:	PSTC – 101	
- Stainless Steel	15 minute dwell 24 hour dwell	80 oz/in (88 N/100 mm) 96 oz/in (105 N/100 mm)
- Powder coated surfaces *	15 minute dwell 24 hour dwell	72 oz/in (80 N/100 mm) 90 oz/in (100 N/100mm)
- Polyethylene	15 minute dwell 24 hour dwell	50 oz/in (55 N/100 mm) 55 oz/in (60 N/100 mm)
Shear Adhesion to:	PSTC – 107	
- Stainless Steel	1/2” x 1/2” x 1000g	2 hours
Tack	PSTC - 6 Rolling Ball Tack	< 2 inches



## PROPERTIES (Continued)

PHYSICAL PROPERTIES	TEST METHODS	NOMINAL RESULTS
Coefficient of Friction (Kinetic)	ASTM D1894 Dry Rubber Wet Rubber Dry Leather Wet Leather	1.2 1.1 0.9 1.2
Service Temperature High	14 days at 150°F	No Visible effects
Low	14 days at -20°F	No Visible effect

CHEMICAL PROPERTIES	REAGENT	RECOMMENDATION
<u>Solvent Resistance</u> <i>(Product laminated to stainless steel panel and allowed to condition for 24 hrs at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for 1 hour at room temperature then reagent is removed and product is immediately tested for scrape resistances, delaminating, and other visual effects.)</i>	Water 10% Salt Water Bleach Trichloroethylene 25% Sulfuric Acid 1% Sodium Hydroxide Unleaded Gasoline Diesel Fuel Hydraulic Fluid 50% Antifreeze in water MEK Mineral Spirits 99% IPA	Recommended Recommended Intermittent Contact Only Not Recommended Not Recommended Recommended Not Recommended Not Recommended Recommended Recommended Not Recommended Intermittent Contact Only Not Recommended

\* Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains, and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.

**Note:** While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.

## WARRANTY

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability for specific applications.

