

Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove :

Virtex™ 79-700

	Chemical Agent	Breakthrough Time	Protection Index	CAS Number	Notified Body	EN Standard
	Acetic Acid, Glacial	9	0	64-19-7	Centexbel	374-3:2003
	Acetone	< 5	0	67-64-1	Centexbel	374-3:2003
	Acetonitrile	< 5	0	75-05-8	Centexbel	374-3:2003
	Acrylic Acid	< 5	0	79-10-7	Centexbel	374-3:2003
	Ammonium Hydroxide, 25%	24	1	1336-21-6	Centexbel	374-3:2003
	Benzene	< 5	0	71-43-2	Centexbel	374-3:2003
	Butyl Acetate	< 5	0	123-86-4	Centexbel	374-3:2003
	Chromic Acid, 50%	> 180	4	11115-74-5	Centexbel	374-3:2003
	Cyclohexanone	6	0	108-94-1	Centexbel	374-3:2003
	Diethylamine	< 5	0	109-89-7	Centexbel	374-3:2003
	Dimethylacetamide	8	0	127-19-5	Centexbel	374-3:2003
	Dimethylformamide	< 5	0	68-12-2	Centexbel	374-3:2003
	Ethanol, 95%	15	1	64-17-5	Centexbel	374-3:2003
	Ethyl Acetate	< 5	0	141-78-6	Centexbel	374-3:2003
	Formaldehyde, 35%	> 480	6	50-00-0	Centexbel	374-3:2003
	Heptane	> 480	6	142-82-5	Centexbel	374-3:2003
	Hexane	> 480	6	110-54-3	Centexbel	374-3:2003
	Hydrochloric Acid, 37%	166	4	7647-01-0	Centexbel	374-3:2003
	Hydrofluoric Acid, 48%	9	0	7664-39-3	Force Technology	374-3:2003

Permeation breakthrough times according to EN374-3:2003 (minutes)

0	1	2	3	4	5	6
< 10	10-30	30-60	60-120	120-240	240-480	> 480
Not recommended	Splash protection		Medium protection		High protection	

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Ansell Healthcare Europe N.V. (European Head Office)

Riverside Business Park, Block J

Boulevard International 55, 1070 Brussels, Belgium

Tel. +32 (0) 2 528 74 00 • Fax +32 (0) 2 528 74 01 • Fax Customer Service +32 (0) 2 528 74 03

<http://www.ansell.eu> • E-mail info@ansell.eu



Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove :

Virtex™ 79-700

	Chemical Agent	Breakthrough Time	Protection Index	CAS Number	Notified Body	EN Standard
	Hydrogen Peroxide, 30%	140	4	7722-84-1	Centexbel	374-3:2003
	Iso-Octane	> 480	6	540-84-1	Centexbel	374-3:2003
	Isopropanol	96	3	67-63-0	Centexbel	374-3:2003
	Methanol	6	0	67-56-1	Centexbel	374-3:2003
	Methyl ethyl ketone	< 5	0	78-93-3	Centexbel	374-3:2003
	Nitric Acid, 70%	< 5	0	7697-37-2	Centexbel	374-3:2003
	Peracetic acid, 39%	20	1	79-21-0	Centexbel	374-3:2003
	Perchloroethylene	12	1	127-18-4	Centexbel	374-3:2003
	Sodium Hydroxide, 40%	> 480	6	1310-73-2	Centexbel	374-3:2003
	Styrene	< 5	0	100-42-5	Centexbel	374-3:2003
	Sulphuric acid, 96%	13	1	7664-93-9	Centexbel	374-3:2003
	Toluene	< 5	0	108-88-3	Centexbel	374-3:2003
	Triethylamine	100	3	121-44-8	Centexbel	374-3:2003
	Xylene	< 5	0	1330-20-7	Centexbel	374-3:2003

Permeation breakthrough times according to EN374-3:2003 (minutes)

0	1	2	3	4	5	6
< 10	10-30	30-60	60-120	120-240	240-480	> 480
Not recommended	Splash protection		Medium protection		High protection	

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Ansell Healthcare Europe N.V. (European Head Office)

Riverside Business Park, Block J

Boulevard International 55, 1070 Brussels, Belgium

Tel. +32 (0) 2 528 74 00 • Fax +32 (0) 2 528 74 01 • Fax Customer Service +32 (0) 2 528 74 03

<http://www.ansell.eu> • E-mail info@ansell.eu

